

# HC260LA

# Micro-alloyed steel grades with high yield strength for cold forming

| Material no. | 1.0480        |
|--------------|---------------|
| according to | DIN EN 10268, |
|              | Edition 10/06 |

## Chemical composition<sup>1)</sup>

(in percent by weight)

|    | min.in % | max. in %          |
|----|----------|--------------------|
| С  |          | 0.1                |
| Si |          | 0.5                |
| Mn |          | 1.0                |
| Р  |          | 0.030              |
| S  |          | 0.025              |
| ΑΙ | 0.015    |                    |
| Ti |          | 0.15 <sup>2)</sup> |
| S  | 0.015    | 0.025              |

#### 1) Heat analysis

2) These additional elements may be added single or in combination, if they are contained in the specification of the steel grade and the mass fraction being within the permissable limits. Vanadium can also be added. The total of the mass fractions of all three elements shall not exceed 0.22%.

### Mechanical properties (transverse)

| Yield strength R <sub>eL</sub> /R <sub>p 0,2</sub> in MPa |          |  |
|---|----------|--|
| 260 -   | -330 MPa |  |
|   |          |  |
| Tensile strength R <sub>m</sub> in MPa                    |          |  |
| 350 -   | -430 MPa |  |
|   |          |  |
| Total elongation $A_{80}$ in $\%$                         |          |  |
| ≥ 26  | %        |  |
|   |          |  |

Products according to this European Standard must meet the requirements for transverse test pieces as given in table 2.

It may be agreed that the requirements for longitudinal test pieces, as given in table 3, shall be valid instead of those for transverse test pieces.

#### Available dimensions

| Thickness in mm | Width in mm |
|-----------------|-------------|
| 0.50 - 0.59     | 900 - 1,300 |
| 0.60 -3.00      | 900 - 1,850 |

#### Surface finish

The steel grade is available in the surface finishes A and 03.

Commitments regarding certain properties or a certain purpose of use require written agreements. Technical changes as well as typesetting and printing errors reserved.



 $\label{eq:Salzgitter} \textbf{Salzgitter Flachstahl GmbH} / \texttt{Eisenh\"{u}} ttenstraße 99 / 38239 \texttt{Salzgitter} \\ \textbf{PHONE} + 49 (0) 53 41 21 28 90 / \texttt{FAX} + 49 (0) 53 41 21 85 36 / \texttt{MAIL} flachstahl@salzgitter-ag.de www.salzgitter-flachstahl.de} \\$