



HC420LA+ZE

Steel grades with high yield strength
for cold forming - micro alloyed

Material no.	1.0556
according to	DIN EN 10268

Chemical Composition

(in percent by weight)

	min. in %	max. in %
C		0.14
Si		0.5
Mn		1.6
P		0.030
S		0.025
Al	0.015	
Nb		0.09
Ti		0.15 ¹⁾

1) These additional elements may be added single or in combination, if they are contained in the specification of the steel grade and the mass fraction being within the permissible limits.

Vanadium can also be added. The total of the mass fractions of all three elements shall not exceed 0.22%.

Mechanical properties (transverse)

Yield strength $R_{eL}/R_{p0.2}$ in MPa
420 - 520
Tensile strength R_m in MPa
470 - 590
Total elongation A_{80} in %
≥ 17

The samples for the tensile test are taken at right angles to rolling direction unless the product width is opposed to this.

Available dimensions

Thickness in mm	Width in mm
0.60 - 0.69	1,000 - 1,500
0.70 - 1.39	900 - 1,600
1.40 - 2.00	900 - 1,700
2.01 - 2.35	900 - 1,600
2.36 - 2.50	900 - 1,500

Surface finish

Micro-alloyed steel grades with higher yield points can only be supplied with surface finish A and O3 respectively.

Commitments regarding certain properties or a certain purpose of use require written agreements. Technical changes as well as typesetting and printing errors reserved.

