

# HC340LA Micro-alloyed steel grades with high yield strength for cold forming

0.030

0.025

0.092)

0.1572)

Material no.	1.0548	Mechanical properties (transverse)
according to	DIN EN 10268,	
	Edition 10/06	Yield strength $R_{eL}/R_{p\ 0,2}$ in MPa
		340 - 420
Chemical composition <sup>1)</sup>		Tensile strength $R_m$ in MPa
(in percent by w	eight)	410 - 510
min. in S	% max. in %	Total elongation $A_{80}$ in $\%$
С	0.12	≥ 21
Si	0.5	
Mn	1.5	Products acording to this European Sta

ean Standard must meet the requirements for transverse test pieces as given in table 2.

It may be agreed that the requirements for longitudinal test pieces, as given in table 3, shall be valid instead of those for transverse test pieces.

### Available dimensions

Thickness in mm	Width in mm
0.50 - 0.59	900 - 1,300
0.60 - 0.69	900 - 1,400
0.70 - 1.29	900 - 1,700
1.30 - 3.00	900 - 1,850

## Surface finish

The steel grade is available in the surface finishes A and 03.

#### 1) Heat analysis

0.015

Ρ

S

ΑI

Nb

Ti

2) These additional elements may be added single or in combination, if they are contained in the specification of the steel grade and the mass fraction being within the permissable limits. Vanadium can also be added. The total of the mass fractions of all three elements shall not exceed 0.22%.

#### Commitments regarding certain properties or a certain purpose of use require written agreements. Technical changes as well as typesetting and printing errors reserved.



Salzgitter Flachstahl GmbH / Eisenhüttenstraße 99 / 38239 Salzgitter PHONE +49(0)53 41 21 28 90 / FAX +49(0)53 41 21 85 36 / MAIL flachstahl@salzgitter-ag.de www.salzgitter-flachstahl.de