

FolaSal® – PVDF – coating system

Description:

A two-layer coating system consisting of primer and top coat. The usual overall layer thickness is 25 µm. Coating thicknesses up to 50 µm are available. This coating system has a satisfying weather stability and excellent forming properties. Because of the excellent UV-stability, FolaSal®-PVDF-coatings are suited for the application in climates with a very high UV radiation.

Fields of application:

Sandwich panels and trapezoidal profiles for roofs and walls (exterior) with high requirements regarding colour stability; also garage doors, caravans, road signs and blinds.

Please note:

Our technical customer service is at your disposal for more information about this and our other FolaSal® coating systems.

Properties:

Property	Test specification	Value
Usual overall coating thickness	DIN EN 13523-1	25 µm
Gloss (60°)	DIN EN 13523-2	20 – 40 GE
Adhesion (Cross cut)	DIN EN ISO 2409	GT 0
Adhesion after indentation	DIN EN 13523-6	6mm/ GT 0
Resistance to cracking on bending (adhesion)	DIN EN 13523-7	max. 1T without peeling
Resistance to cracking on bending (flexibility)	DIN EN 13523-7	max. 3T without cracks
Resistance to solvents (rubbing test)	DIN EN 13523-11	at least 100 double friction (not for metallics)
Pencil hardness	DIN EN 13523-4	HB-F
Buchholz indentation test	DIN EN ISO 2815	min. 80
Resistance to rapid deformation (Impact test)	DIN EN 13523-5	min. 8J
Resistance to salt spray	DIN EN ISO 9227 DIN EN ISO 4628-2 DIN EN ISO 4628-8	after 360h the average delamination (corrosion creep) at the scribe is max. 2 mm, no blistering on the surface
Temperature stability		up to 80°C, temporary up to 110°C
Minimum processing temperature		18°C (material temperature)
Corrosion protection class	DIN 55928-8	KIII (in combination with Z275)

All data given in this document comply with our current technical expertise and our experiences. The data sheet can only be a means of non-committal consultancy. We do not accept any liabilities whatsoever regarding completeness and accuracy. It does not release the customer from his due diligence while handling the goods. As the given data are non-binding, we will not accept any legal charges. The latest available issue can be found on our homepage www.salzgitter-flachstahl.de.