

## S350GD

Hot-dipped galvanised, pre-painted  
structural steels for cold forming

Material no.	1.0529
according to	DIN 17162/2
	DIN EN 10326

### Chemical composition

(in percent by weight)

	min.	max.
C		0.200 %
Si		0.600 %
Mn		1.700 %
P		0.100 %
S		0.045 %

### Mechanical properties <sup>1)</sup>

Yield strength $R_{eL}/R_{p0.2}$	$\geq 350$ MPa
Tensile strength $R_m$	$\geq 420$ MPa
Total elongation $A_{80}$	$\geq 16$ %

The samples for the tensile test are taken at right angles to rolling direction unless the product width is opposed to this.

1) All given mechanical properties refer to the carrier material before painting.

### Available dimensions <sup>1)</sup>

Thickness in mm	Width in mm
0.45 <sup>2)</sup> – 0.50 <sup>2)</sup>	900 – 1,450
0.50 – 0.70	900 – 1,450
0.71 – 0.80	900 – 1,500
0.81 <sup>2)</sup> – 0.87 <sup>2)</sup>	900 – 1,500
0.88 <sup>2)</sup> – 1.95 <sup>2)</sup>	900 – 1,550
1.96 <sup>2)</sup> – 3.00 <sup>2)</sup>	900 – 1,420

1) The maximum cross-section (product: width x thickness) may not exceed 2,800 mm<sup>2</sup>.

2) By prior agreement

### Coating systems

#### Varnish <sup>1)</sup>

SP	Polyester (interior and exterior)
SP-PA	Polyamide modified polyester
HDP	High durable polyester
HDP-PA	polyamide mod. high dur. polyester
PVDF	Polyvinylidenfluoride
PUR	Polyurethane
PUR-PA	polyamide modified polyurethane
EP	Epoxide

#### Foils <sup>2)</sup>

PVC (F)	Polyvinylfluoride foil
PVF (F)	Polyvinylfluoride foil tedlar®

1) Further steel grades with coating systems on request.

2) Foils available only single-sided.