

Technical Product Information Hot-rolled Sheets

Normal flatness equates to the normal deviation on the plate as per EN 10051.

Flatness type **seca®** warrants the following maximum flatness deviations **on the plate**:

Flatness type **seca®xtra** warrants the following maximum flatness deviations on the plate and on the cut component:

Strength class A	
Nominal width w	Normal flatness
≤ 1,200 mm	15 mm
1,200 < w ≤ 1,500 mm	18 mm
> 1,500 mm	23 mm

Strength class A	
Nominal width w	seca®
≤ 1,200 mm	5 mm
1,200 < w ≤ 1,500 mm	6 mm
> 1,500 mm	8 mm

Strength class A	
Nominal width w	seca®xtra
≤ 1,200 mm	5 mm
1,200 < w ≤ 1,500 mm	6 mm
1,500 < w ≤ 1,800 mm	8 mm

Strength class B	
Nominal width w	Normal flatness
≤ 1,200 mm	18
1,200 < w ≤ 1,500 mm	23
> 1,500 mm	28

Strength class B	
Nominal width w	seca®
≤ 1,200 mm	6 mm
1,200 < w ≤ 1,500 mm	8 mm
> 1,500 mm	9 mm

Strength class B	
Nominal width w	seca®xtra
≤ 1,200 mm	6 mm
1,200 < w ≤ 1,500 mm	8 mm
> 1,500 mm	9 mm

Strength class C	
Nominal width w	Normal flatness
≤ 1,200 mm	23 mm
1,200 < w ≤ 1,500 mm	30 mm
> 1,500 mm	38 mm

Strength class C	
Nominal width w	seca®
≤ 1,200 mm	8 mm
1,200 < w ≤ 1,500 mm	10 mm
> 1,500 mm	12 mm

Strength class C	
Nominal width w	seca®xtra
≤ 1,200 mm	8 mm
1,200 < w ≤ 1,500 mm	10 mm
> 1,500 mm	12 mm

Strength class D	
Nominal width w	Normal flatness
≤ 1,200 mm	23 mm
1,200 < w ≤ 1,500 mm	30 mm
> 1,500 mm	38 mm

Strength class D	
Nominal width w	seca®
≤ 1,200 mm	8 mm
1,200 < w ≤ 1,500 mm	10 mm
> 1,500 mm	12 mm

Strength class D	
Nominal width w	seca®xtra
≤ 1,200 mm	8 mm
1,200 < w ≤ 1,500 mm	10 mm
> 1,500 mm	12 mm

All flatness deviations apply for nominal thickness t : $2 \leq t \leq 16$ mm

In addition to the product range, the categories A and B can be produced from 5 mm thickness in widths up to 2,000 mm.

The said warrant postulate a proper handling with respect to storage and transport of the material.